

DOW-MITSUI POLYCHEMICALS CO., LTD.

Tokyo Midtown Yaesu, Yaesu Central Tower 19F
2-1, Yaesu 2-Chome, Chuo-ku, Tokyo 104-0028, Japan

TEL: +81-3-6880-7650

EVAFLEX™ EV40WH

- Ethylene-vinyl acetate Copolymer Resin-

Property	Test Method	Units	EV40WH
VA Content	JIS K7192	wt%	41
Melt Flow Index	JIS K7210	g/10min	65
Density	JIS K7112	kg/m ³	970
Tensile strength @ Break	JIS K7161	MPa	3
Tensile elongation @ Break	JIS K7161	%	>1,000
Stiffness	JIS K7106	MPa	1
Hardness (Shore A)	JIS K7215	-	49
Vicat Softening Point	JIS K7206	°C	< 30
Melting Point	DSC	°C	49

The data shown are typical values and should not be used for specifications.



DOW-MITSUI POLYCHEMICALS CO.,LTD.