



# PT. INKOMAS LESTARI

Office / Factory : Jl. Jababeka X Blok G No. 34 – 35

Kawasan Industri Jababeka,

Cikarang, Bekasi 17530, Indonesia

Telp. : +62-21-8934026

Fax. : +62-21-8934096

Website : [www.inkomas.com](http://www.inkomas.com)

## **InkomaS<sup>®</sup> IL 3101 S**

**HS No. 2915.70.30**

### **LEAD STEARATE**



#### ***PROPERTIES***

- Appearance : White Fine Powder
- Lead Content :  $27.5 \pm 0.5$  %
- Free Fatty Acid : 1.0 % max.
- Moisture : 0.5 % max.
- Trough 140 Mesh Sieve : 95.0 % min
- Melting Point :  $105.0 \pm 5.0$  °C.

#### ***CHARACTERISTICS***

- Good Heat Stability and excellent external lubricity.
- Offers excellent synergistic effects when use with BaSt or CaSt.

#### ***PACKING***

- 20 kgs. net in PE / PP woven bag.

#### ***STORAGE***

- Keep in dry cool storage is recommended.
- Once opened packing should be firmly closed.

#### ***CAUTION***

- All necessary safety precautions in handling Lead Compound must be strictly adhered to.