

INTAFIRE 6137

Description	: Flame retardant masterbatch
Application	: Injection, blown film
Carrier Resin	: Polyethylene
Addition level	: 7% for injection. 15% for film

Physical Properties

Item	Test Method	Unit	Product Specification
MFI	ASTM D – 1238 (190 °C / 5 kg)	g / 10 min	5 – 10
Specific Gravity	JIS K 7112	-	2.00 – 2.20
Moisture Content	ASTM D 6980-12	%	< 0.1

Packaging

INTAFIRE 6137 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

Storage

INTAFIRE 6137 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product.

03/VIII/23/INTAFIRE6137

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.