

EXTRUSION THERMOFORMING

We provide materials and products that are key to advanced solutions to modern challenges



MAS **2158**

MAS 2158 is high quality homopolymer polypropylene resin in pellet form for thin extrusion thermoforming application such as drinking cups, beverage cups, etc



- Drinking cups
- Jelly cups
- Sheets
- Trays

CHARACTERISTICS:

- · Excellent impact strength
- Outstanding processability
- Odorless



Head Office:

Jl. Jend. Sudirman Kav. 10-1 MidPlaza 2, 20th floor Jakarta 10220, Indonesia P:+62 21 5703883 F:+62 21 5704689

Plant Site:

Jl. Raya Juntinyuat Km. 13 Kecamatan Juntinyuat Kabupaten Indramayu P:+62 234 428 002 F:+62 234 428 616

www.polytama.co.id





PHYSICAL PROPERTIES:

Application	Unit	Standard Method	Typical Value
Melt Flow Index	gram/10 min	ASTM D1238/L	1.8
Tensile Strength at Yield	Mpa	ASTM D638	> 34
Elongation at Yield		ASTM D638	>8
Flexural Modulus	Mpa	ASTM D747	> 1400
Notched Izod Impact	J/m	ASTM D256	> 45
Density	gram/cm³	ASTM D1505	< 0.91
Total Volatiles		PP 15754	< 0.1
Melting Temperature	°C	DSC	165
HDT at 66 psi	°C	ASTM D648	92 - 95
Vicat Softening Temperature	°C	ASTM D1525L	152 - 155

- * Values presented are typical laboratory average. Actual values may vary within moderate range.
- ** Improvements or amendments may apply to any product without alteration to the product code

REGULATORY COMPLIANCE

This product complies to domestic and international recommendations and regulations regarding safety of materials used for food packaging, such as:

- ISO 22000 : 2015 for Food Safety Management System
- SNI No. 0594: 2011 about Polypropylene
- BPOM RI Regulation No HK. 03.1.23.07. 11.6664 in 2011 about Supervision of Food Packaging
- · CONEG Legislation on Packaging Material in the United States 2012 about Heavy Metal Content
- Halal Certification from Majelis Ulama Indonesia (Indonesian Council of Ulama)