

## **Product Data**

Developmental Data

## TITANPRO **PM602** FOR MULTIFILAMENT SPUNBOND

- CHARACTER Polypropylene homopolymer. The base resin meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520(a)(1)(i) and (c)1.1a. TSCA Registry: CAS# 9003-07-0.
- APPLICATIONS High speed fine denier fiber production. Spunbond nonwoven fibers. Multifilament fibers.
- ADVANTAGES High melt flow and good drawability. High gloss. Narrow molecular weight distribution. Excellent spinning performance. Anti-gas fading.
- **FABRICATION** Equipment general extrusion machines. Techniques - standard processing.

TYPICAL RESIN PROPERTIES (a)	<u>UNIT</u>	<u>PM602</u>	ASTM METHOD <sup>(b)</sup>
Melt Flow Rate, at 230°C	g/10 min	35	D1238
Density	g/cm <sup>3</sup>	0.9	D1505
Tensile Strength at Yield	kg/cm²	330	D638
Elongation at Yield	%	13	D638
Flexural Modulus	kg/cm²	13000	D790B
Notched Izod Impact Strength at 23°C	kg·cm/cm	3	D256A
Heat Deflection Temperature at 4.6 kg/cm <sup>2</sup>	°C	104	D648
Rockwell Hardness	R scale	100	D785A
Water absorption after 24 hours	%	0.02	D570

(a) Values shown are average and are not to be considered as specifications.(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 1.3 - 1.4% depending on the product wall thickness and molding parameters.

D03

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.