



INTAKALK 803

Description	: Calcium Carbonate masterbatch	
Base Resin	: Polyethylene	
CaCO ₃ content	: 80 %	
CaCO ₃ particle size	: D50 2 micron	
Application	: Extrusion, Blow Molding, Blown film	

Physical Properties

ITEM	TEST METHOD	UNIT	PRODUCT
			SPECIFICATION
MFI	ASTM D – 1238 (190°C / 10 kg)	g / 10 min	2-6
Specific Gravity	JIS K 7112	-	1.92 – 2.12
Moisture Content	ASTM D 6980-12	%	< 0.1
Appearance	visual		Opaque pellet

Packaging

INTAKALK 803 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven bag as outer layer.

Storage

INTAKALK 803 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product.

02/IV/23/KALK803

www.interapolimer.com

The data contained in this safety data sheet are based on our current knowledge and experience and describe the product only with regard to safety requirements. This safety data sheet is neither a Certificate of Analysis (CoA) nor technical data sheet and shall not be mistaken for a specification agreement. Identified uses in this safety data sheet do neither represent an agreement on the corresponding contractual quality of the substance/mixture nor a contractually designated use. It is the responsibility of the recipient of the product to ensure any proprietary rights and existing laws and legislation are observed.

PT INTERA LESTARI POLIMER

Jakarta Jl. Kesehatan No. 48, Jakarta 10160 P : +62 21 38 901 901 F : +62 21 38 901 890 Bandung Jl. Sukamenak No. 97 Bandung 40227 P : +62 22 8780 2277 F : +62 22 541 9594 Surabaya Jl. Berbek Industri II No. 4, Sidoarjo 60293 P : +62 31 843 8484 F : +62 31 847 5350

info@interapolimer.com