

HLGP850S

General-Purpose Polystyrene Technical Datasheet

Features

- higher MFR
- suitable for extrusion and injection molding
- high transparency with blue tint
- thin and glossy

End uses

- excellent for all kinds of daily commodities
- food containers, water cups
- glossy cap layer on HIPS sheet
- lampshade

Compliant to

- US FDA 21 CFR.177.1640
- EU RoHS 2011/65/EU
- REACH Regulation 1907/2006


Certified by

REACH

HLGP850S				
Property	Unit	Specification	Result	Test Method
Melt Mass-Flow Rate	g/10min	7.5~8.5	8.1	GB/T3682.1-2018
Tensile Strength	MPa	≥45	48.5	GB/T1040.2-2022
Charpy Index Strength	kJ/m ²	≥7.8	8.0	GB/T1043.1-2008
Vicat Softening Temperature	°C	≥90	96	GB/T1633-2000
Temperature of Deflection under Load	°C	≥85	89	GB/T1634.2-2019
Residual Styrene Monomer	mg/kg	≤400	330	GB/T16867-1997
Light Transmittance	%	≥89	90	GB/T2410-2008
Molding Shrinkage	%	0.3~0.6	0.5	GB/T17037.4-2003
Conclusion	Grade A			

All tests were run under laboratory conditions.

The data are intended as a general guide only.



HENGLI

Hengli Energy & Chemical (Shanghai)