



COLMASTER BLUE 977

Description : Blue masterbatch

Application : Blown Film, Blow Molding, Extrusion

Carrier resin : Polyethylene

Addition level : 2-3%

Physical properties:

Item	Test Method	Unit	Standard Specification
MFI	ASTM D – 1238 (190 °C / 2.16 kg)	g / 10 min	2 - 3
Specific Gravity	JIS K 7112	-	1.18 - 1.30
Moisture content	ASTM D 6980-12	%	< 0.1
Heat resistance	Based on Pigment Specification	°C	250
Light Fastness	Based on Pigment Specification	1 - 8	8
Weather Fastness	Based on Pigment Specification	1 - 5	5
Resin Application	Based on Pigment Specification	-	LDPE, LLDPE,
			HDPE, PP

Packaging

COLMASTER BLUE 977 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

Storage

COLMASTER BLUE 977 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product

01/VII/20/COL977

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

PT INTERA LESTARI POLIMER

www.interapolimer.com

info@interapolimer.com

P:+62 31 8438484 F:+62 31 8475350