

## Product Data

### TITANLENE LDC800YY FOR EXTRUSION COATING

<b>CHARACTER</b>	LDC800YY is a low density polyethylene resin for extrusion coating and is a barefoot grade. LDC800YY meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 2.1 & (c) 2.2.
<b>APPLICATIONS</b>	Coating for all substrates.
<b>ADVANTAGES</b>	Good drawdown, good heat sealability and adhesion properties.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>TITANLENE LDC800YY</u> <sup>(a)</sup>	<u>ASTM METHOD</u> <sup>(b)</sup>
Melt index	g/10 min	<b>3.5</b>	D1238
Density	g/cm <sup>3</sup>	<b>0.920</b>	D1505
Vicat softening point	°C	<b>87</b>	D1525
Neck-in (constant output 50m/min, 295°C)	cm	<b>8</b>	(c)
 <b><u>BARRIER PROPERTIES</u></b>			
MVTR(90%RH, 37.8°C, 25µm)	g/m <sup>2</sup> /24h	<b>18</b>	F372
O <sub>2</sub> GTR	10 <sup>4</sup> cm <sup>3</sup> µm m <sup>2</sup> 24hr atm	<b>22</b>	D3985

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) Internal method

#### Processing conditions

Melt temperature : 270 - 340°C

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R00