

Topilene® J446H

Polypropylene Copolymer
For Injection Molding Applications

Product Description

Topilene® J446H is a heterophasic copolymer, suitable for injection moulding applications which features good impact property. The product used in a large variety of applications, such as houseware, crates, stackable boxes and toy articles.

Characteristics

Typical Application Crates, Caps & Closures, Sports, Leisure and Toys, Housewares

Features Impact Copolymer / High impact strength / Wide application

Typical Properties

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	4.0	g/10min
Density	ASTM D792	0.90	g/cm ³
Tensile Strength at Yield	ASTM D638	220	kg/cm ²
Flexural Modulus	ASTM D790	12,500	kg/cm ²
Notched Izod Impact Strength(23°C)	ASTM D256	No break	kg-cm/cm

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG VINA CHEMICALS CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG VINA CHEMICALS CORPORATION. **Topilene®** is a registered trademark owned or used by HYOSUNG VINA CHEMICALS CORPORATION.

Contacts

Head Office Lot 01CN ~ 08CN, Cai Mep Industrial Park,
Tan Phuoc Ward, Phu My Town, Ba Ria Vung Tau
Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online www.hyosungchemical.com
www.topilene.com