

CEESBE PRO



Product Data Sheet CEESBE PRO (Calcium Carbonate Masterbatch)

CP - BL

1. Specification			
PROPERTIES	TEST METHOD	UNIT	STANDARD
Specific Gravity	ASTM D 792	g/cm ³	± 1,90
MFI (190°C/2.16 kg)	ASTM D 1238	gr/10 min	≥ 1,0
CaCO ₃ Content	Maker's own	%	82 ±1,0
Moisture Content	Maker's own	%	≤ 0,20
Pellet Size	Maker's own	mm	2 - 3 mm
Carrier	Maker's own	-	PE
2. Application 2.1. Use for		Blow Molding Injection Molding	
2.2 The recommended rate		Up to 35%	
3. CaCO₃		2.0 Micron (2.000 Mesh)	
4. Packing		25 Kg Nett In PP Bag	

* Recommended Processing Conditions :

Melt Temperature170 - 230°C

* Recommended Rate;

Basic Resin

Ratio (weight)

Blow Molding;

HDPE
PP

Up to 30%
Up to 35%

Injection Molding;

HDPE
PP

Up to 25%
Up to 35%

 **PT CAVE Sumber Berkah**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A
Kp. Cilampeni RT 002/ RW 006 Cilampeni Katapang
Bandung 40971, Indonesia

Phone : + 6 2 2 2 5 8 9 7 4 5 8 Facs : + 6 2 2 2 5 8 9 7 4 5 7
Email : cavesh@bdg.centrin.net.id



REDUCE COST..!



It is To Be Green