

# CEESBE PRO



## Product Data Sheet CEESBE PRO ( Calcium Carbonate Masterbatch )

### CP - MA

1. Specification			
PROPERTIES	TEST METHOD	UNIT	STANDARD
Specific Gravity	ASTM D 792	g/cm <sup>3</sup>	± 1,90
MFI ( 190°C/2.16 kg )	ASTM D 1238	gr/10 min	≥ 1,0
CaCO <sub>3</sub> Content	Maker's own	%	83 ±1,0
Moisture Content	Maker's own	%	≤ 0,20
Pellet Size	Maker's own	mm	2 - 3 mm
Carrier	Maker's own	-	PE + PP
2. Application			
2.1. Use for			Film PP Yarn Injection ( Low Loading )
2.2 The recommended rate			5 - 30 %
3. CaCO <sub>3</sub>			3.5 Micron ( 1.200 Mesh )
4. Packing			25 Kg Nett In PP Bag

\* Recommended Processing Conditions :

Melt Temperature .....170 - 230°C

\* Recommended Rate;

	Basic Resin	Ratio ( weight )
Blown Film;	HDPE	Up to 15%
Flat Yarn	PP	Up to 15 %
Injection Molding;	HDPE	Up to 15%
	PP	Up to 20%
Monofilament	LDPE	10 - 30%
	PP	10 - 30%
Band	LDPE	5%
	PP	5%

 **PT CAVE Sumber Berkas**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A  
Kp. Cilampeni RI 002/ RW 006 Cilampeni Katapang  
Bandung 40971, Indonesia

Phone : + 62 22 5897458 Facs : + 62 22 5897457  
Email : cavesh@bdg.centrin.net.id

 **REDUCE COST..!**

 **It is To Be Green**