

# CEESBE PRO



## Product Data Sheet

### CP-PH

1. Specification			
PROPERTIES	TEST METHOD	UNIT	STANDARD
Specific Gravity	ASTM D 792	g/cm <sup>3</sup>	± 1,90
MFI ( 230°C/2.16 kg )	ASTM D 1238	gr/10 min	≥ 5,0
CaCO <sub>3</sub> Content	Maker's own	%	75,±1,0
Moisture Content	Maker's own	%	≤ 0,20
Pellet Size	Maker's own	mm	2 - 3 mm
Carrier	Maker's own	-	PE + PP
2. Application			
2-1. Use for			PP Yarn ( High Speed & High Dossage )
2-2 The recommended rate			Up to 35%
3. CaCO <sub>3</sub>			1.1 Micron ( 2.500 Mesh )
4. Packing			25 Kg Nett In PP Bag

\* Recommended Processing Conditions :

Melt Temperature ..... 180 - 250°C

\* Recommended Rate;

Basic Resin

Ratio ( weight )

Flat Yarn

PP

Up to 35 %

 **PT CAVE Sumber Berkat**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A  
Kp. Cilampeni RT 002/ RW 006 Cilampeni Katapang  
Bandung 40971, Indonesia

Phone : + 62 22 5897458 Facs : + 62 22 5897457  
Email : cavesh@bdg.centrin.net.id

 **REDUCE COST..!**

 **It is To Be Green**