

CEESBE PRO



Product Data Sheet

CP-PM

1. Specification			
PROPERTIES	TEST METHOD	UNIT	STANDARD
Specific Gravity	ASTM D 792	g/cm ³	± 1,90
MFI (230°C/2.16 kg)	ASTM D 1238	gr/10 min	≥ 4,0
CaCO ₃ Content	Maker's own	%	82,±1,0
Moisture Content	Maker's own	%	≤ 0,20
Pellet Size	Maker's own	mm	2 - 3 mm
Carrier	Maker's own	-	PE + PP
2. Application			
2-1. Use for			PP Yarn (High Loading)
2-2 The recommended rate			Up to 25%
3. CaCO ₃			2.0 Micron (2.000 Mesh)
4. Packing			25 Kg Nett In PP Bag

* Recommended Processing Conditions :

Melt Temperature180 - 250°C

* Recommended Rate;

Basic Resin

Ratio (weight)

Flat Yarn

PP

Up to 25 %

 **PT CAVE Sumber Berkat**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A
Kp. Cilampeni RT 002/ RW 006 Cilampeni Katapang
Bandung 40971, Indonesia

Phone : + 6 2 2 2 5 8 9 7 4 5 8 Facs : + 6 2 2 2 5 8 9 7 4 5 7
Email : cavesh@bdg.centrin.net.id

 **REDUCE COST..!**

 **It is To Be Green**