

CEESBE PRO




Product Data Sheet CEESBE PRO (Calcium Carbonate Masterbatch)

CP - SB

1. Specification		
PROPERTIES	UNIT	STANDARD
Specific Gravity	g/cm ³	± 1,90
CaCO ₃ Content	%	75,±1,0
MFI (230°C/2.16 kg)	gr/10 min	≥ 15,0
Moisture Content	%	≤ 0,20
Melting Point	Celsius	130°C
Pellet Size	mm	2 - 3 mm
Carrier		PP
2. Application		
2.1. Use for		PP Non Woven Injection Molding
2.2 The recommended rate		5 - 30 %
3. CaCO₃		Nano
4. Packing		25 Kg Nett In PP Bag

1. Recommended Processing Conditions : Melt Temperature170 - 230°C

2. Recommended Rate;	Basic Resin	Ratio (weight)
PP Non Woven;	PP	Up to 30 %
Injection Moulding;	HDPE	Up to 20 %
	PP	Up to 30 %

 **PT CAVE Sumber Berkas**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A
Kp. Cilampeni RI 002/ RW 006 Cilampeni Katapang
Bandung 40971, Indonesia

Phone :+ 62 22 5897458 Facs :+ 62 22 5897457
Email : cavesh@bdg.centrin.net.id

 **REDUCE COST..!**

 **It is To Be Green**