

CEESBE PRO



Product Data Sheet CEESBE PRO (Calcium Carbonate Masterbatch)

CP - SF

1. Specification		
PROPERTIES	UNIT	STANDARD
Specific Gravity	g/cm ³	± 1,90
Ash Content	%	75,±1,0
MFI (230°C/2.16 kg)	gr/10 min	≥ 20,0
Moisture Content	%	≤ 0,20
Melting Point	Celsius	130°C
Pellet Size	mm	2 - 3 mm
Carrier		PP, PE
2. Application		
2.1. Use for		Injection Molding Lamination Coating PP Non Woven
2.2 The recommended rate		5 - 25 %
3. CaCO ₃		Nano
4. Packing		25 Kg Nett In PP Bag

 **PT CAVE Sumber Berkat**

KOMPLEK INDUSTRI TRIKENCANA KAV. 12A
Kp. Cilampeni RT 002/ RW 006 Cilampeni Katapang
Bandung 40971, Indonesia

Phone : + 62 22 5897458 Facs : + 62 22 5897457
Email : cavesh@bdg.centrin.net.id

 **REDUCE COST..!**

 **It is To Be Green**