

TECHNICAL DATA SHEET

ISO 9001 : 2015 Scoope of Certification MANUFACTURING OF RECYCLED PLASTICS Certificate No : ID003528







HDPE BLOWN MOULDING RED d HDPE BLOWN MOULDING RED

Description

High Density Polyethylene (HDPE) in blue pellet, produced from post consumer bottle and jerry can.

Application

This product is suitable mostly for all blown film applications. Product is typically used in:

- Bottles, Including for industrial chemicals or oils.
- Natural gas distribution pipe system.

Material Properties			
	Test Method	Value	Unit
Physical			
Density	ISO 1183	0.95 - 0.98	g/cm³
Ash content	ISO 3451	< 1	%
Tensile Strength	ISO 527	min 15	MPa
Elongation	ISO 527	min 100	%
Melt Temperature Range		150 - 170	°C
Rheological			
Melt Flow Rate (190 °C / 2.16 kg)	ISO 1133	0.10 - 0.50	g/10 min
Melt Flow Rate (190 °C / 5.00 kg)	ISO 1133	0.60 - 1.00	g/10 min
Other			
Moisture Content		< 1	%
Filtration		100	mesh

Note:

The information is offered solely as a guide for your consideration and investigation based on our current knowledge and experience. Product properties may be changed without notice. These properties are should not be construed as binding specifications limits or minimum values The suitability of the data for a specific processing method can only be ensured with investigations and tests by the end user.

> FACTORY: Raya Desa Sumput, Kec. Driyorejo, Gresik 61177, INDONESIA Tel: +62 31 759 1000 (Hunting), 759 0202 Fax: +62 31 759 2020 Email: info@pelitamekarsemesta.com Web: www.pelitamekarsemesta.com

> > Revised date: 31 May 2024