# **LF410**

# Low-density polyethylene (LDPE)



## **General Information**

LF410 is an Low-density polyethylene resin produced in the tubular process, Designed for film, foamed and has excellent processability, excellent optical properties, and mechanical properties

### **Key Features**

- Excellent processability and mechanical properties
- Low Fish Eye
- Excellent optical properties
- Slip, Anti-blocking properties
- Heat seal

#### **Applications**

• General Blown film, Foamed

**Properties** 

Item		Measuring Method		Value	Unit	
Physical	Melt Flow Index (190°C, 2.16kg)		ASTM	D1238	2.0	g/10min
	Density		ASTM	D1505	0.923	g/cm <sup>3</sup>
Mechanical	Tensile Stress (Yield)		ASTM	D638	110	kgf/cm <sup>2</sup>
Film (50µm)	Tensile Strength (Break)	MD	ASTM	D882	250	kgf/cm <sup>2</sup>
		TI			210	kgf/cm <sup>2</sup>
	Elongation (Break)	ME	ASTM	D882	250	%
		TI			600	%
	Elmendorf Tear Strength	MD Ti	ASTM	D1922	180 280	q q
	Dart Drop Impact Strength, F50		ASTM	D1709	110	g
	<b>Coefficient of Friction</b>		ASTM	D1894	< 0.2	
	Haze		ASTM	D1003	< 8	%
Thermal	Melting Point		LC Method		110	°C
	VICAT Softening Point		ASTM	D1525	93	°C

<sup>•</sup> NOTE : Physical Properties : these are not to be construed as specifications

<sup>\*</sup> Disclaimer: All information in this document is for reference only and is not a final product specification. Before using our products, the customer must determine for himself the suitability, safety and legality of the intended use. We do not assume any liability or responsibility for the use of this document or the contents of this document, and we reserve the right to change the contents of this document arbitrarily without prior notice.



<sup>•</sup> Process Condition : Tmpeature : 170℃, BUR : 2.5, Film Thickness 50µm