

COIM Asia Pacific Pte Ltd Novacote Flexpack Division 10 Seraya Place Jurong Island Singapore 627843 Telephone (65) 68967068 Telefax (65) 6896 7065



## **TECHNICAL DATA SHEET**

## Novacote NC-7105 + CA-27 LAMINATING ADHESIVE

| PRODUCT DESCRIPTION      | • | Novacote NC-7105+CA-27 is a solvent-based 2-component polyester<br>polyurethane adhesive for dry bond laminating of film/film, film/metallized<br>films and film/foil structures. Novacote NC-7105 + CA-27 shows high heat<br>and product resistance properties in laminates. |            |                  |             |            |  |
|--------------------------|---|---|------------|------------------|-------------|------------|--|
| PRODUCT REFERENCE        | : | NC- 7105<br>(-OH component)   |            | CA-27<br>Co-read | ctant (-NCO | component) |  |
| SOLID CONTENT            | : | (75 ± 2) %  |            | (75 ± 2)         | (75 ± 2) %  |            |  |
| VISCOSITY                | : | 6000-12000 mPas at 25 °C 1200-3000 mPas at 25   |            | 5 °C             |             |            |  |
| DILUENT                  |   | Ethyl Acetate (urethane grade only).  |            |                  |             |            |  |
| MIX RATIO BY WEIGHT      | : | Running solids  |            |                  |             |            |  |
|                          |   |   | <u>25%</u> | <u>30%</u>       | <u>35%</u>  | <u>40%</u> |  |
|                          |   | NC-7105 :   | 100        | 100              | 100         | 100        |  |
|                          |   | Ethyl acetate :   | 230        | 173              | 131         | 101        |  |
|                          |   | CA-27 :   | 15         | 15               | 15          | 15         |  |
|                          |   | Total (kg)  | 345        | 288              | 246         | 216        |  |
|                          |   | Viscosity at 25°C<br>DIN 4 Cup (sec)  | 12         | 13               | 15          | 17         |  |
| DILUTION<br>INSTRUCTIONS | : | Mix NC-7105 + Ethyl Acetate first followed by co-reactant, CA-27.   |            |                  |             |            |  |
| DYNAMIC PAN-LIFE         | : | 24 hours (tested 35% running solids in ethyl acetate at 35 °C/100% rh)  |            |                  |             |            |  |
| APPLICATION METHOD       | : | Gravure coating or smooth roll coating.   |            |                  |             |            |  |
| DRYING CONDITIONS        | : | Forced hot air (60-90 °C) sufficient to remove the solvent. Exhaust must be efficient to remove solvent vapours from the drying tunnel.   |            |                  |             |            |  |
|                          |   |   |            |                  |             |            |  |
| NIP TEMPERATURE          | : | 50-70 °C  |            |                  |             |            |  |
| DRY COATING WEIGHT       | : | 2-4 gsm   |            |                  |             |            |  |

.....2/

The information provided herein is to our best knowledge true and accurate. However, we cannot accept liability for any recommendation or representation made, since the conditions and methods of application are beyond our control. These are typical physical properties, not manufacturing specifications. For health and safety requirements, please refer to the Material Safety Data Sheets (MSDS).

## Novacote NC-7105 + CA-27 LAMINATING ADHESIVE

| CURING TIME                | : | Bond immediately off the machine is good. Maximum heat and product resistance will develop within 5-10 days. Higher curing temperatures (e.g., 40 °C for 3-5 days) will accelerate curing rate, and give better heat and product resistance properties.  |
|----------------------------|---|--|
| PRE-TREATMENT OF<br>FILMS  | : | For polyolefin films, corona treatment is mandatory. Pretreatment will<br>improve the results obtained with polyester film and some nylon films.<br>Recommended corona treatment level on common films is as follows: PE,<br>PP films: 38 dynes/cm; PET, O-Ny: 52 dynes/cm; metallized films: 38-40<br>dynes/cm.   |
| STORAGE AND SHELF-<br>LIFE | : | NC-7105 and CA-27 are flammable liquids. Store under dry conditions at 5 - 30°C, and away from direct sunlight. Close the containers after each use especially co-reactant, which is highly moisture-sensitive. Use up the products as soon as possible once the containers are open. Otherwise, purging of the containers with dry air or nitrogen gas is recommended. Shelf life is 6 months in original unopened containers stored away from heat, direct sunlight and rain.  |
| FDA STATUS                 | : | Novacote NC-7105 + CA-27 complies with US FDA Regulation,<br>21 CFR § 175.105 (Adhesives for food packaging materials).  |
| IMPORTANT NOTE             | : | Before we introduce a new adhesive to the marketplace, the adhesive is<br>comprehensively tested in our own laboratories. However, because of the<br>hundreds of possible film combinations and the different printing ink<br>systems used in various parts of the world, as well as the diversity of food,<br>cosmetics, medical devices and pharmaceuticals that may be packaged in<br>laminates made with our adhesive, we <u>cannot</u> possibly forecast their<br>performance under all circumstances. Therefore, we strongly urge our<br>customers to test our adhesive on a small scale to establish that laminates<br>made with our adhesive are suitable for the end uses for which they are<br>intended, prior to commencing large scale production. |

Revised: 06/14