

DOW-MITSUI POLYCHEMICALS CO., LTD.

Shiodome City Center
5-2, Higashi-Shimbashi 1-chome
Minato-Ku, Tokyo 100-7117, Japan

TEL: 81-3-6253-4000
FAX: 81-3-6253-4262

EVAFLEX™ EV260

Property	Test Method	Units	EV260
VA Content	JIS K7192	wt%	28
MFR	JIS K7210	g/10min	6
Density	JIS K7112	Kg/m ³	950
Tensile Strength	JIS K7161	MPa	21
Elongation	JIS K7161	%	800
Stiffness	JIS K7108	MPa	17
Hardness(Shore A)	JIS K7215	Degree	80
Vicat Softening Point	JIS K7208	°C	41
Melting Point	JIS K7121	°C	72

The data shown are typical values and should not be used for specifications.



Dow-Mitsui Polychemicals
A DOW COMPANY