

ADVANCED PRODUCT DATA SHEET



MFR 9.5

Density 954 **ETILINAS TRIMOD AMT5531B**

High Density Polyethylene for Blow Moulding

DESCRIPTION

ETILINAS TRIMOD AMT5531B is a high density polyethylene with an excellent combination of stiffness and ESCR and a good impact resistance. It is delivered in pellet form and contains antioxidants. Typical customer applications include jerry cans for the packaging of dangerous goods and light weight jerry cans.

CHARACTERISTICS include:

- High molecular weight HDPE
- Excellent balance stiffness to ESCR
- Excellent impact strength

APPLICATIONS include:

- Special grade for packaging, technical parts
- Jerry Can, Containers 2-15 liters for dangerous goods

Product Properties	Test Method	Units	Value
Density (23°C, base resin)	ISO 1183-1/A	g/cm ³	0.954
Melt Flow Rate 190/5	ISO 1133	g/10 min	0.43
Melt Flow Rate 190/21.6	ISO 1133	g/10 min	9.5
FFR (MFR 21.6kg/MFR 5kg)	ISO 1133	-	22
Tens. Mod. (23°C, v = 1mm/min, Sec.)	ISO 527-2	MPa	1200
Tensile Impact Strength (23°C, notched)	ISO 8256-1A	kJ/m ²	145
Tensile Impact Strength (-30°C, notched)	ISO 8256-1A	kJ/m ²	≥60
Charpy Impact Strength (-30°C, notched)	ISO 179-1/1eA	kJ/m ²	7
ESCR (FNCT, 4 MPa, 80°C, 2% NP9*)	ISO 16770	h	>18

Typical Processing Conditions

Recommended melt temperature on processing: 180-220°C

Notes:

*NP9: Arkopal N100, Igepal BC9

ADVANCED PRODUCT DATA SHEET



MFR 9.5

Density 954 **ETILINAS TRIMOD AMT5531B**

High Density Polyethylene for Blow Moulding

AVAILABILITY

ETILINAS TRIMOD AMT5531B is available in 25kg bag and bulk bag. The product type and batch number are clearly marked on each bag.

STORAGE/HANDLING

ETILINAS TRIMOD AMT5531B should be properly stored in well ventilated environment at a temperature of below 50°C. Prolonged or improper storage can result in deterioration of product properties. The PETRONAS Chemicals Safety Data Sheet (SDS) contains important safety information and should be viewed before using the product.

HEALTH & SAFETY

ETILINAS TRIMOD AMT5531B is not classified as a dangerous preparation. Please refer to our Safety Data Sheet (SDS) for details on various aspects of safety, recovery and disposal of the product.

PRODUCT STEWARDSHIP

PETRONAS aims to increase awareness of all the hazards associated with the storage, handling and use of its products. Thoroughly reviewing the accompanying Safety Data Sheets and disseminating the information to all dependent and interested parties is an essential part of any 'Responsible Care' programme.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

- Safety Data Sheet (SDS)
- Statement on chemicals, regulations and standards

FOR MORE INFORMATION

Please contact **PETRONAS Chemicals Group Berhad (PCGB)**, Level 34, Tower 1, PETRONAS TWIN TOWER, KLCC, 50088 KUALA LUMPUR, MALAYSIA.

Tel: +(603) 2051 5000 Fax: +(603) 2051 1501 or visit our website www.petronaschemicals.com

IMPORTANT NOTICE

Information contained in this document is accurate and reliable to the best of the knowledge and belief of PETRONAS Chemicals Group Berhad (PCGB). The suggestions and recommendations offered herein serve as a guide in the use of these materials, and cannot be guaranteed because the conditions of use are beyond PCGB's control. PCGB assumes no responsibility for the use of information supplied, the application, adaptation or processing of the products described herein and here by disclaims all liability (except as otherwise provided by the law) in regard to such use.