



# PT HALIM SAMUDRA INTERUTAMA

SALES OFFICE ADDRESS : JL. TOMANG RAYA NO. 4 JAKARTA 11430 – INDONESIA  
TELP. : 021-5600400, 5660708 FAX. : 021-5600390, 5667440, E-mail : [hsp@halim-sakti.com](mailto:hsp@halim-sakti.com)  
FACTORY : JL. INDUSTRI RAYA IV BLOK AE NO. 10-BUNDER CIKUPA, KAB. TANGERANG, 15710 BANTEN-INDONESIA  
TELP. : 021-5903992 (HUNTING) , FAX. : 0215900268, E-mail : [hasiu@centrin.net.id](mailto:hasiu@centrin.net.id) , NPWP (TAX ID ) : 01.061.869.2-052.000

## TECHNICAL DATA SHEET NO. 006 S – QA/PET/VIII – 31/22

**COMMODITY** : HAIPET  
**GRADE** : #70  
**COLOR** : NATURAL  
**APPEARANCE** : PELLET FORM  
**DATE** : AUGUST 31, 2022

### PHYSICAL PROPERTIES

TEST ITEM	UNIT	TEST METHOD	TES VALUE
			#70
MELT INDEX (E TYPE 190°C , 2.16 Kg)	g / 10 min	ASTM D 1238	1 – 3
SPECIFIC GRAVITY	--	ASTM D 792	1.90
CaCO <sub>3</sub> CONTENT	%	MAKER'S STD	86
MOISTURE CONTENT	%	MAKER'S STD	MAX. 0.2
DISPERSION TEST	--	MAKER'S STD	PASS
CaCO <sub>3</sub> PARTICLE SIZE	MESH	MAKER'S STD	800
CARRIER RESIN	--	--	HDPE + LLDPE
APPLICATION	--	--	PP INJECTION HDPE, LLDPE FILM

- ALL DATA ARE DETERMINED ON INJECTION AND ANNEALED AT 23°C AND 50% RELATIVE HUMIDITY UNLESS OTHERWISE

**QUALITY CONTROL DEPARTMENT**

**QUALITY CONTROL DEPARTMENT**