

Technical Data Sheet



HIPS BLACK

Description

High Impact Polystyrene (HIPS) in black flakes, products from the postal industry and from the industrial consumer sheets.

Application

This product is suitable for all parts of the automotive industry electronic components for all Electronic hardware products.

Material Properties			
	Test Method	Value	Unit
Physical			
Density	ISO 1183	0.98 - 1.00	g/cm³
Rheological			
Melt Flow Rate (200 °C / 5.00 kg)	ISO 1133	2.91 - 3.99	g/10 min
Ash content	ISO 3451	< 1	%
Tensile Strength	ISO 527	2.54	mm²
	ISO 527	55.24	N (F max)
	ISO 527	21.71	MPa
Other			
Moisture Content		<1	%
Melt Temperature Range		190 - 250	°C

Note:

The information is offered solely as a guide for your consideration and investigation based on our current knowledge and experience. Product properties may be changed without notice. These properties are should not be construed as binding specifications limits or minimum values. The suitability of the data for a specific processing method can only be ensured with investigations and tests by the end user.

FACTORY: Raya Desa Sumput, Kec. Driyorejo, Gresik 61177, INDONESIA Tel: +62 31 759 1000 (Hunting), 759 0202 Fax: +62 31 759 2020 Email: info@pelitamekarsemesta.com Web: www.pelitamekarsemesta.com