



# **INTANOX PE 1068**

Description	: Anti Oxidant Masterbatch		
Application	: Blown film, Extrusion, Injection Molding, Blow Molding		
Carrier Resin	: Polyethylene		
<b>Addition Level</b>	: 1 - 4 %		

## **Physical Properties**

ITEM	TEST METHOD	UNIT	PRODUCT SPECIFICATION
Melt Flow Index	ASTM D – 1238 ( 190 <sup>0</sup> C / 2.16 kg )	g / 10 min	40 - 70
Specific Gravity	JIS K 7112	-	0.85 - 0.95
Moisture Content	ASTM D 6980-12	%	< 0.1

### Packaging

INTANOX PE-1068 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

### Storage

INTANOX PE-1068 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product.

#### 03/VI/21/INTANOX-PE1068

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

PT INTERA LESTARI POLIMER

Jakarta Jl. Kesehatan No. 48, Jakarta 10160 P : +62 21 38 901 901 F : +62 21 38 901 890 Bandung Jl. Sukamenak No. 97 Bandung 40227 P : +62 22 8780 2277 F : +62 22 541 9594 Surabaya Jl. Berbek Industri II No. 4, Sidoarjo 60293 P : +62 31 843 8484 F : +62 31 847 5350

www.interapolimer.com

info@interapolimer.com