

## INTRABLACK HG 9688

<b>Description</b>	: Black Masterbatch
<b>Application</b>	: Extrusion, blown film, blow moulding, injection moulding.
<b>Carrier Resin</b>	: Polyethylene
<b>Addition Level</b>	: 0.5 - 3 % (Injection-Thicker Application) 3 – 6 % (Blown Film-Thinner Application)

### Physical Properties

ITEM	TEST METHOD	UNIT	PRODUCT SPECIFICATION
Melt Flow Index	ASTM D – 1238 ( 190 °C / 10 kg )	g / 10 min	1 – 8
Specific Gravity	JIS K 7112	-	1.13 – 1.23
Moisture Content	ASTM D 6980-12	%	≤ 0.14

### Packaging

INTRABLACK HG 9688 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

### Storage

INTRABLACK HG 9688 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product.

04/VII/20/HG 9688

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.