

INTRASLIP PE 59

Description	: Slip agent masterbatch
Application	: Blown film, extrusion.
Carrier Resin	: Polyethylene
Addition Level	: 1 - 3 %

Physical Properties

Item	Test Method	Unit	Product Specification
MFI	ASTM D – 1238 (190 °C / 2.16 kg)	g / 10 min	10 – 25
Specific Gravity	JIS K 7112	-	0.86 – 0.96
Moisture Content	ASTM D 6980-12	%	< 0.1

Packaging

MASTERBATCH INTRASLIP PE 59 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

Storage

MASTERBATCH INTRASLIP PE 59 should be stored in a dry environment. Opened bag should be kept tightly to prevent contamination of the product.

02/IX/21/MB-SLIP-PE59

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

PT INTERA LESTARI POLIMER

www.interapolimer.com

info@interapolimer.com

Jakarta
Jl. Kesehatan No. 48, Jakarta 10160
P : +62 21 38 901 901
F : +62 21 38 901 890

Bandung
Jl. Sukamenak No. 97 Bandung 40227
P : +62 22 8780 2277
F : +62 22 541 9594

Surabaya
Jl. Berbek Industri II No. 4, Sidoarjo 60293
P : +62 31 843 8484
F : +62 31 847 5350