

INTRAWHITE 12 C 75

- Description** : Economical grade of white masterbatch contains high quality TiO₂.
- Application** : Film / sheet extrusion, blown film, blow moulding, injection moulding.
- Carrier Resin** : Polyethylene
- Addition Level** : 1 - 4 %

Physical Properties

Item	Test Method	Unit	Product Specification
Melt Flow Index	ASTM D – 1238 (190 °C / 2.16 kg)	g / 10 min	1 - 10
Specific Gravity	JIS K 7112	-	1.60 - 1.90
Moisture Content	ASTM D 6980-12	%	< 0.1
Food Contact Approval	BBKK Method		Yes

Packaging

Intrawhite 12C75 is supplied in pellet form, in 25 kgs double layered bags, consisting of plastic PE bag as inner layer and PP woven laminated paper bag as outer layer.

Storage

Intrawhite 12C75 should be stored in a dry environment, and not exceed 12 months for optimum performance. Opened bag should be kept tightly to prevent contamination of the product.

02/IX/21/12C75

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of utilization of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

PT INTERA LESTARI POLIMER

www.interapolimer.com

info@interapolimer.com

Jakarta
 Jl. Kesehatan No. 48, Jakarta 10160
 P : +62 21 38 901 901
 F : +62 21 38 901 890

Bandung
 Jl. Sukamenak No. 97 Bandung 40227
 P : +62 22 8780 2277
 F : +62 22 541 9594

Surabaya
 Jl. Berbek Industri II No. 4, Sidoarjo 60293
 P : +62 31 843 8484
 F : +62 31 847 5350