



PT KRISTAL POLIMER INDO
Tel. +62 21 5862038
Fax. +62 21 5862038
Email. Kristalpolimerindo@gmail.com
Office and Manufacture :
Surya Balaraja Blok F No.19
Jl. Raya Serang Km 28
Balaraja, Tangerang - Indonesia

TECHNICAL DATA SHEET

PRODUCT NAME	: MASTERBATCH WHITE 9002T
APPEARANCE	: BLUEISH OPAC WHITE
APPLICATION	: INJECTION & BLOW MOULDING, EXTRUSION SHEET, BLOWN FILM
USAGE PERCENTAGE	: AS REQUIRED, COMMONLY 2%
RESIN CARRIER	: LLDPE
RESIN SUITABILITY	: PP, PE, HIPS
HEAT STABILITY	: 250 °C
LIGHT STABILITY	: 7 (Wool Scale 8-1)
WEATHER STABILITY	: 4 (Grey Scale 5-1)
FOOD CONTACT	: APPROVED
SPECTROPHOTOMETERS (DE)	: $L^* = 94,88$; $a^* = -1,08$; $b^* = -0,83$

Note : These data above are obtained according to our best experience and should be used as a guide only, not as a guarantee.



PT KRISTAL POLIMER INDO
Tel. +62 21 5862038
Fax. +62 21 5862038
Email. Kristalpolimerindo@gmail.com
Office and Manufacture :
Surya Balaraja Blok F No.19
Jl. Raya Serang Km 28
Balaraja, Tangerang - Indonesia

TECHNICAL DATA SHEET

PRODUCT NAME	: MASTERBATCH WHITE 8109
APPLICATION	: EXTRUTION SHEET, BLOWN FILM, INJECTION & BLOW MOULDING
ADDITION PERCENTAGE	: AS REQUIRED, COMMONLY 2%
RESIN CARRIER	: LLDPE
RESIN SUITABILITY	: PP, PE, HIPS
HEAT STABILITY	: 300 °C
LIGHT STABILITY	: 7 (Wool Scale 8-1)
WEATHER STABILITY	: 4 (Grey Scale 5-1)
FOOD CONTACT	: APPROVED
PELLET COUNT	: 30-50 pcs/gr
MELT FLOW INDEX (190°C, 2.16kg)	: 52 gr/10mnt

Note : These data above are obtained according to our best experience and should be used as a guide only, not as a guarantee.