



PT HALIM SAMUDRA INTERUTAMA

SALES OFFICE ADDRESS : JL. TOMANG RAYA NO. 4 JAKARTA 11430 - INDONESIA

TELP. : 021-5600400, 5660708 FAX. : 021-5600390, 5667440, E-mail : hsp@halim-sakti.com

FACTORY : JL. INDUSTRI RAYA IV BLOK AE NO. 10 - BUNDER CIKUPA, KAB. TANGERANG, 15710 BANTEN - INDONESIA

TELP. : 021-5903992 (HUNTING) , FAX. : 021-5900268, E-mail : hasiu@centrin.net.id, NPWP (TAX ID) : 01.061.869.2-052.000

TECHNICAL DATA SHEET NO. 010 S – QA / TER / XII – 06 / 22

COMMODITY : HAIMASTER
GRADE : MB
COLOR / NO. COLOR : BLUE 7399
APPEARANCE : PELLET FORM
DATE : DECEMBER 06, 2022

PHYSICAL PROPERTIES

TEST ITEM	UNIT	TEST METHOD	TEST VALUE
			BLUE 7399
MELT INDEX (E TYPE 190°C , 2.16 Kg)	g/ 10 min.	ASTM D-1238	3 - 12
PARTICLE SIZE	--	MAKER'S STD	2 - 3
MOISTURE CONTENT	%	MAKER'S STD	MAX. 0.2
PIGMENT CONTENT	%	MAKER'S STD	35
DISPERSION TEST	--	MAKER'S STD	PASS
CARRIER RESIN	--	--	LLDPE
APPLICATION	--	--	PP,PE INJECTION HDPE FILM/YARN PP FILM/YARN LLDPE FILM

- THESE TYPICAL PROPERTIES VALUES ARE INTENDED TO SERVE AS GUIDE ONLY, AND NOT AS SPECIFICATION LIMITS.

QUALITY CONTROL DEPARTMENT