



PT HALIM SAMUDRA INTERUTAMA

SALES OFFICE ADDRESS : JL. TOMANG RAYA NO. 4 JAKARTA 11430 – INDONESIA
TELP. : 021-5600400, 5660708 FAX. : 021-5600390, 5667440, E-mail : hsp@halim-sakti.com
FACTORY : JL. INDUSTRI RAYA IV BLOK AE NO. 10-BUNDER CIKUPA, KAB. TANGERANG, 15710 BANTEN-INDONESIA
TELP. : 021-5903992 (HUNTING) , FAX. : 0215900268, E-mail : hasiu@centrin.net.id , NPWP (TAX ID) : 01.061.869.2-052.000

TECHNICAL DATA SHEET

NO.014 T – QA / TER / XI – 07 / 25

COMMODITY : HAIMASTER
GRADE : MB
COLOR / NO. COLOR : WHITE 116
APPEARANCE : PELLET FORM
DATE : NOVEMBER 07, 2025

PHYSICAL PROPERTIES

TEST ITEM	UNIT	TEST METHOD	TEST VALUE
			WHITE 116
MELT INDEX (E TYPE 190°C, 2.16 Kg)	g/ 10 min.	ASTM D-1238	MIN. 1
MOISTURE CONTENT	%	MAKER'S STD	MAX. 0.2
DISPERSION TEST	--	MAKER'S STD	PASS
TiO2 CONTENT	--	MAKER'S STD	55
CARRIER RESIN	--	--	PE
APPLICATION	--	--	PP,PE INJECTION LLDPE, HDPE FILM PP FILM

- THESE TYPICAL PROPERTIES VALUES ARE INTENDED TO SERVE AS GUIDE ONLY, AND DOES NOT CONSTITUTE AS GUARANTEE.

QUALITY CONTROL DEPARTMENT