

PRODUCT DATA SHEET

PH512

POLYPROPYLENE HOMOPOLYMER

Product Description

PH512 is a homopolymer with a good melt flow and stiffness suitable to be used for general purpose injection moulding applications.

Characteristics

- Medium flow
- Medium stiffness

Applications

- Caps & closures
- Housewares & rigid packaging items

Properties

Typical Properties	Test Method	Units	Typical Value
Physical			
Melt Flow Rate @ 230 °C/2.16 kg	ISO 1133	g/10min	12
Density	ISO 1183	g/cm ³	0.90
Mechanical			
Flexural Modulus	ISO 178	MPa	1475
Tensile Modulus	ISO 527-2	MPa	1550
Tensile Stress at Yield	ISO 527-2	MPa	35
Tensile Strain at Break	ISO 527-2	%	>50
Tensile Strain at Yield	ISO 527-2	%	10
Impact			
Izod Notched @ 23 °C min	ISO 180/1A	kJ/m ²	3.4
Thermal			
Vicat Softening Temperature (A/50N)	ISO 306	°C	153
Heat Deflection Temperature B (0.45MPa, Unannealed)	ISO 75B-2	°C	95

Note: The above are typical data representing the product; not to be construed as analysis certificate or specifications. User should confirm results by their own tests.

Typical Processing Conditions

PH512 can be processed on most standard injection moulding conversion equipment designed for PP. Optimization may be required depending on the exact end use requirement. Recommended melt temperature in the range of 190–240°C can be used.

Regulatory Information

Details of information will be provided in a relevant declaration letter upon request.

Processing and Handling

PH512 should be stored in a dry, under shaded and ventilated environment at a temperature below 50°C. Prolonged or improper storage can result in deterioration of product properties.

Health and Safety

This product is not classified as a dangerous preparation. Before using this product, customer is advised to consult PRefChem's Safety Data Sheet (SDS) to understand the precautions in various aspect of safety, recovery and disposal of the product.

For More Information

Please contact:

Pengerang Petrochemical Company Sdn. Bhd. (201501003532 (1128864-H))

First Floor, Administration Block A2, Pengerang Integrated Complex Management Office (PICMO), 81600 Pengerang, Johor. Website: www.prefchem.com

Disclaimer: Information in this document is accurate to the best of our knowledge at the date of publication. The information may change as a result of production and testing upon production. This product data sheet is given in a good faith without any express or implied representation of the end usage of the products. It is expected that user(s) throughout the value chain may use this product in combination with products of other manufacturer(s), henceforth PRefChem accepts no responsibility or liability for results obtained by the application of this information or the safety and suitability of these products, either alone or in combination with other products. Therefore they are advised to make their own tests at their own costs to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, PRefChem sells these products without warranty, and user(s) throughout the value chain assume all responsibility and liability including associated third party claims for loss or damage arising from the handling and use of products, whether used alone or in combination with other products.