



**KASAKATA**  
MASTERBATCH

## **KASALEN SLIP AGENT FC0214**

**TECHNICAL INFORMATION**

### **APPLICATION**

General Application  
Polyolefin

### **CHEMICAL DESCRIPTION**

Primary Fatty Amide

### **SUGGESTED DOSAGES**

1-2 % for general purpose  
application

### **ACTIVE AGENT**

1000 - 1200 ppm active  
agent per 1% dosage

### **PROPERTIES**

- Very effective slip agent for polyolefin.
- Primary fatty amide as active from vegetable.
- Translucent white granules.
- Food contact.

### **ADVANTAGES**

- Provide high slip at low dosage level.
- Reduce friction in plastic caps and closures to allow easier application and removal of the part.
- Also act as mold release and scuff resistance.

### **PHYSICAL PROPERTIES**

• <b>Appearance</b>	Translucent White
• <b>Melting Point</b>	120°C
• <b>Specific Gravity</b>	Min. 0.8
• <b>Granule Size</b>	2.0 - 3.0 mm in length and 2.0 - 3.0 mm in diameter

### **REGULATORY COMPLIANCE**

#### **USA**

- US Food and Drug Administration (FDA)

#### **EUROPE**

- EU commission regulation 10/2011, food contact

#### **INDONESIA**

- Halal Certified

Note :

The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding