

## Product Data

### TITANLENE LDC801YY FOR EXTRUSION COATING

**CHARACTER** LDC801YY is a low density polyethylene resin for extrusion coating and is a barefoot grade. LDC801YY meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 2.1 & (c) 2.2.

**APPLICATIONS** Coating for all substrates.

**ADVANTAGES** Excellent drawdown, good heat seability and adhesion properties.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>TITANLENE LDC801YY</u> <sup>(a)</sup>	<u>ASTM METHOD</u> <sup>(b)</sup>
Melt index	g/10 min	7	D1238
Density	g/cm <sup>3</sup>	0.920	D1505
Vicat softening point	°C	86	D1525
Neck-in (constant output 50m/min, 295°C)	cm	9	(c)

#### BARRIER PROPERTIES

MVTR(90%RH, 37.8°C, 25µm)	g/m <sup>2</sup> /24h	18.5	F372
O <sub>2</sub> GTR	10 <sup>4</sup> cm <sup>3</sup> µm m <sup>2</sup> 24h atm	23	D3985

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) Internal method

#### Processing conditions

Melt temperature : 270 - 340°C

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R00